

Suppressed Hysteretic Field Emission from Polymer Encapsulated Silver Nanowires

Matthew T. Cole, Sahin Coskun, Richard J. Parmee, Pritesh Hiralal, Cinzia Cepek, Alexander W. Robertson, Chi Li, Qing Dai, Jamie H. Warner, William I. Milne, & Husnu E. Unalan

Abstract— Suppression of the hysteretic electron emission in one-dimensional nanomaterial-based electron sources remains a critical barrier preventing their wide scale adoption in various vacuum electronics applications. Here we report on the suppressed hysteretic performance, and its photo-dependence from conformal poly-vinylpyrrolidone (PVP) encapsulated percolative Ag nanowire (NW)-based electron sources.

Index Terms—silver nanowires, field electron emission, adlayer, hysteresis, poly-vinylpyrrolidone

I. INTRODUCTION

THE field of vacuum electronics is undergoing a renaissance. With significant interest in the application of field electron emission in flat panel displays, parallel electron beam lithography systems, space propulsion, chemical analysis, microwave amplifiers, lighting, and X-ray sources[1-5], the integration and rational synthesis of nanoscale systems is allowing otherwise challenging emission geometries to be realized via near atomic-scale self-assembly. Nanomaterials are continuing to find ever more varied and diverse applications in the field of vacuum electronics. Though many proposed ideas are technologically unfeasible, the use of the myriad nanowire (NW) types in electron emission devices has significant potential, principally due to their intrinsically high aspect ratios[6, 7]. Nevertheless, such systems remain plagued by hysteresis within their electron emission, which significantly degrades the cycle-to-cycle reproducibility of the transport. Various suggestions have been put forth as to the source of such hysteresis within nanoscale electron emission systems, including; back-bombardment from desorbed ionized species[8] and subsequent micro-plasma mediated morphological deformation, emission from transient intermediate energy states[9], dynamic bias ramp-rate effects, transient emitter field-dependent electrostatic alignment[10], deep level carrier capture,

oxide charging, and trap de-population[11]. Others have attributed such hysteresis effects to both reversible[12] and irreversible structural changes[13] in the emitters. The detailed underpinning mechanism remains largely unclear, though it likely stems collectively from many of these sources. Though certainly not all, most mechanisms proposed relate to the fine physiochemistry of the emitters surface. Emitter encapsulation has been shown elsewhere to enhance the temporal stability of various one-dimensional nanoscale electron sources [14, 15], with various polymer adlayers[16-20] evidencing potential as emission enhancing and hysteresis suppressing over-coatings. Here, via broadband optical excitation, we investigate the hysteretic field emission performance of percolative networks of poly-vinylpyrrolidone (PVP) encapsulated Ag NWs.

II. RESULTS & DISCUSSION

Figure 1 illustrates the electron source fabrication procedure. All chemicals were purchased from Sigma-Aldrich and were used without further purification. Ag NWs were synthesized according to our previously reported method[21]; 10 mL, 0.45M EG solution of PVP (MW = 55000, [C₆H₉NO]_n) was prepared with 7 mg NaCl (99.5%). The solution was heated to 170°C in




Fig. 1. Fabrication of the PVP stabilized electron sources via (a) PVP adlayer forming, (b) encapsulated Ag NW synthesis, (c) spray coating (Inset depicts a typical PVP/Ag NW dispersion), and the resulting (d) stabilised electron source.

This work was supported in part by the Oppenheimer Research Trust, Cambridge University, and an Impact Acceleration grant from the Engineering and Physical Sciences Research Council.

M. T. Cole, R. J. Parmee, P. Hiralal and W. I. Milne are with the Department of Engineering, Electrical Engineering Division, University of Cambridge, Cambridge CB3 0FA, United Kingdom. (e-mail: mtc35@cam.ac.uk)

W. I. Milne is with the College of Information Sciences & Electronic Engineering, Zhejiang University, Hangzhou, 310027, China. (e-mail: wim1@cam.ac.uk)

Copyright © 2016 IEEE. Personal use of this material is permitted. However, permission to use this material for any other purposes must be obtained from the IEEE by sending a request to pubs-permissions@ieee.org.

Materials Engineering, Middle East Technical University, 06800, Ankara, Turkey. (e-mail: unalan@metu.edu.tr)

C. Cepek is with the Istituto Officina dei Materiali - CNR, Laboratorio TASC, Area Science Park, Basovizza, I-34149 Trieste, Italy.

C. Li and Q. Dai are with the National Centre for Nanoscience & Technology, Beijing, 100190, China. (e-mail: daiq@nanoctr.cn)

A. W. Robertson and J. H. Warner are with the Department of Materials, University of Oxford, OX1 3PH, United Kingdom.




Fig. 2. (a) Typical Ag NW length and (inset) diameter distribution, the latter of which is here depicted with and without the PVP coating. (b) A scanning electron micrograph of a PVP coated Ag NW network (Scale bar: 5 μm) and (Inset) an optical micrograph of a 10x10 mm sample (Scale bar: 5 mm). (c) A high resolution TEM micrograph of a single Ag NW apex showing the conformation of the PVP adlayer and an interfacial Ag_xO_y layer. (d) XRD spectra of the as-synthesized uncoated Ag NWs and corresponding (Inset) SAED pattern.

a 100 mL bulb and a 0.12M AgNO_3 (99.5%) solution in 5 mL of EG ($\text{C}_2\text{H}_6\text{O}_2$) was prepared and added, dropwise, into the PVP solution by injection pumping (Top-5300 syringe pump) at a rate of 5 mL/h. The solution was magnetically stirred at 1000 rpm throughout. All solutions were kept for a further 30 min at 170°C and were subsequently air-cooled to room temperature. The as-synthesized Ag NW solution was purified using diluted acetone (1:5) with double centrifugation at 8000 rpm for 20 min. NWs were then dispersed in ethanol and again centrifuged at 8000 rpm for an additional 20 min. The final product was dispersed in ethanol for further characterization and processing. To fabricate the electron sources, ethanolic-suspended Ag NWs were deposited onto 200 nm thermally oxidised *p*-doped silicon substrates by nitrogen driven spray coating, with the substrates heated to 120°C on a hot plate. Samples were 10x10 mm with a controlled Ag NW coated area of 9x9 mm. For consistency, a single batch of Ag NWs was used to fabricate all samples investigated in this study. To assess the hysteresis effects of the PVP adlayer it was removed by further annealing at 200°C, for 20 mins in air, with the emission characteristics assessed thereafter.

Ag NWs had a mean diameter of 77.5 ± 9.2 nm and a mean length of 7.32 ± 0.41 μm (Figure 2(a)). Encapsulated samples had a mean PVP thickness of 2.9 ± 0.5 nm. A typical scanning electron micrograph of a fabricated emitter is shown in Figure 2(b) which has a typical areal NW density of $0.143 (\pm 0.009)$ μm^{-2} (Carl Zeiss Gemini 50 scanning electron microscope, 20 kV). Spray coating resulted in no preferential alignment of the

NWs. Ag NW densities exceeded the percolation threshold in all cases. The inset in Figure 2(b) depicts a typical fabricated emitter. Electron micrographs were analysed using the particle analysis tool kit in the freeware, ImageJ. As shown in Figure 2(c), HR-TEM micrographs (FEI Tecnai F20 TEM) suggest the formation of a surface oxide of thickness of around 1 nm, with XRD spectral peaks at 38° and 44° corresponding to the (111) and (200) Ag planes (JCPDS card 04-0783) (Figure 2(d)). Though challenging to assess, the PVP has likely adopted its atactic configuration, with the resulting layer functioning principally as a thin diffusion barrier. HR-TEM reveals that the conformal PVP coating hermetically seals the Ag NWs, largely inhibiting further deleterious trap-forming surface oxidation at STP, though not prior to the unavoidable growth of a native surface oxide during synthesis. Acquired on CsI substrates, FT-IR spectroscopy (Thermo Fischer) revealed that annealing at > 300°C removed all NWs which defined our viable PVP-removing annealing temperature window, with quenching of the C-C (830 cm^{-1}), C-N (1230 cm^{-1}), CH_2 (1448 cm^{-1}), and the broad O-H stretching ($3184\text{-}3568 \text{ cm}^{-1}$) modes suggesting removal of the PVP for temperatures > 200°C. XPS and cross-sectional EDX mapping (LEO 1530 VP GEMINI SEM, 15 kV, Oxford Instruments 7426 detector) showed some (<5%) Au, Cr, Co, and Fe contamination, whilst also highlighting the clearly conformal PVP coating. Scanning electron microscopy and Raman spectroscopy (Renishaw InVia, scanned in triplicate, 515 nm, x50 aperture, incident < 5 mW) of the coated and uncoated samples indicate that though much of the PVP is removed during thermal annealing some agglomerates remain. The enhanced Raman peak at 1573 cm^{-1} has been assigned elsewhere to the C=O stretching mode, indicating that much of the PVP interaction with the underlying Ag NW is mediated through the oxygen limb[22]. Similarly, the enhancement of the 2937 cm^{-1} asymmetric stretch suggests this CH_2 chain is in proximal contact with the Ag NW surface[22], highlighting the PVPs central role in acutely adjusting the surface barrier and hence its critical role in augmenting the electron emission performance given the processes high surface sensitivity.

The PVP adlayer did not dramatically affect the macroscale sheet resistance. Any increase in the inter-NW contact resistance due to the PVP adlayer was largely negligible in that the barrier was sufficiently thin so as to not preclude significant tunnelling between adjacent NWs.

In the present paper, the photo-dependent hysteretic field electron emission performance was extracted from cyclic I-E measurements. As depicted in Figure 3(a), field electron emission studies were conducted in a custom built ultra-high vacuum, turbo molecular pumped to 10^{-8} mbar. The Ag NW samples were grounded and a phosphor coated ITO/glass anode was mounted adjacent to the samples which was positively biased using a computer controlled variable high voltage supply (0-5 kV). Contacts were formed using silver dag. The inter-electrode vacuum gap was fixed and a constant circular emission area of 0.39 cm^2 was used, defined by a 500 μm thick mica restrainer. Measurements were conducted in diode mode with voltage increments of 20-100 V. Each current point was averaged from three separate measurements, following a 3s settling time. Currents were measured using a GPIB interfaced HP 34401A digital ammeter with 6.5-digit precision, independently verified using an array of conventional




Fig. 3. (a) Scheme depicting the diode layout with the incident optical sources shown. (b) Typical hysteresis maps ($\lambda = 445$ nm) for Ag NWs (left) and PVP-coated Ag NWs (right). A turn-on field is noted at around 3 V/ μm . Note the onset on transient instabilities after 31 cycles due to the population of local trap states and likely PVP breakdown. (c) Typical light (broadband) and dark mean I-E curves ($n = 40$) for PVP coated Ag NWs, and the corresponding (inset) Fowler-Nordheim plot for the mean curves.

galvanometric ammeters. More than 6.4×10^5 data points were collected. Each hysteresis map was acquired over 12 hours. Chamber conditions remained unchanged during hysteresis measurements. Sample temperature was monitored using a K-type bimetallic thermocouple. Optical spectra were acquired using an ASEQ Instruments LRI spectrophotometer with a 1 nm resolution. Sample imagery was acquired using a digital

USB interfaced long working distance microscope equipped with a x200 objective.

For X-ray diffraction a Rigaku D/Max-2000 pc diffractometer, fitted with a Cu $K\alpha$ source and operated at 40 kV, was used. For X-ray photoelectron spectroscopy a 120 electron energy analyser at room temperature and a $MgK\alpha_{1,2}$ (1253.6 eV) X-ray source was used, obtaining an overall energy resolution of 0.8 eV. Following annealing, XPS showed a shift of 0.13-0.30 eV in the Ag $3d_{5/2}$ peak, attributed to augmented charge transfer between the Ag NW body and associated adlayers, confirming our thesis that extended annealing effectively removes the PVP adlayer[23], as further verified by in-situ RGA atmospheric analysis during annealing. UPS measurements were acquired using a He II radiation source ($h\nu = 40.8$ eV) with an energy resolution of 0.2 eV. UPS suggested that the work function of the nascent Ag NWs deleteriously increased from 3.37 eV to 3.70 eV for the PVP coated Ag NWs. Though suppressing emission hysteresis, assuming Fowler-Nordheim-like emission, the validity of which remains questionable at the nanoscale, such an increase in WF would deleteriously reduce the beam current. Indeed, our field emission measurements showed a ten-fold decrease in the maximum measured emission current (at 10 V/ μm) upon PVP coating. Similarly, PVP coating deleteriously increased the turn-on field by approximately 1 V/ μm . In Figure 3(b) banding is indicative of hysteretic emission. Though degrading the turn-on, we nonetheless find that the PVP adlayer suppressed hysteretic emission substantially relative to the uncoated Ag NWs, particularly in the high field regime. Our preliminary monochromatic optical excitation studies show an evident hysteresis dependence on excitation wavelength. We attribute this to the formation of a stable interface between the PVP adlayer and the Ag NW. These sealed interfaces likely give rise to less variation, as a function of time, temperature and vacuum conditions, as compared to uncoated Ag NW emission sites. During emission, this passivated interface presents a more robust platform to thermally stimulated changes in the local vacuum environment, as well as local trap population. Further monochromatic wavelength dependent studies will be reported elsewhere.

Figure 3(c) shows the mean and standard deviation (1σ) I-E curves for a PVP coated sample, over 40 cycles, for dark and broadband illuminated conditions. There was a noticeable enhancement in the emission current with illumination, with an increase in emission current of approximately 140% at 10 V/ μm . This is likely an effect of carrier excitation either in the PVP layer or PVP-Ag NW interface. This effect is non-bolometric; no noticeable increase in sample temperature was recorded. In Figure 3(b), odd cycle identifiers represent the field inclination, and even cycle identifiers represent the field declination. The observed electron emission is wholly associated with the Ag NW and Ag NW/PVP dispersions; control studies from uncoated Si and Si/SiO₂ substrates showed emission currents of $< 10^{-9}$ A for electric fields up to 9 V/ μm . PVP/Ag NW samples showed robust and repeatable emission across a wide range of base pressures (10^{-8} - 10^{-3} mbar). The DC temporal stability (24 hrs, 9 V/ μm) of the PVP/Ag NWs was 22.6%, which deleteriously increased to 29.0% under broadband optical excitation. Conversely, a corresponding Gaussian distributed mean emission current during hysteresis

assessment of $0.27 (\pm 0.24) \mu\text{A}$ (dark) and $0.44 (\pm 0.14) \mu\text{A}$ (broadband optical excitation) was noted. During hysteretic measurements for the PVP coated samples it appears that optical excitation increased the absolute magnitude of the emission current but reduced the variability in the emission current. Interestingly, following a conditioning phase (which tended to increase the turn-on field with cycle number) the hysteretic performance of the PVP/Ag NWs in dark conditions was largely stable with cycle number, however; when broadband illuminated, the turn-on field tends to near-monotonically decrease with cycle number at a low rate of $-0.04 \text{ V}\mu\text{m}^{-1}\text{cycle}^{-1}$. Hysteresis was increased by around 50% in the cycle studies upon optical excitation of the PVP coated samples though PVP coating showed, for both dark and illuminated conditions, a clear hysteresis suppression relative to the uncoated Ag NW samples.

III. CONCLUSIONS

In this communication we present our findings on the photo-dependent hysteresis and its suppression in field electron emission from Ag NW electron sources following coating with PVP. Compared to the uncoated Ag NW samples we find a near stable variation in turn-on field with cycle number for our PVP coated samples making the need for emission current feedback control and emitter conditioning redundant in such surface passivated nanoscale systems.

ACKNOWLEDGMENT

M.T.C thanks the Oppenheimer Trust, the Royal Society and the Chinese Academy of Sciences for generous financial support. This work was supported by an Impact Acceleration grant from the Engineering and Physical Sciences Research Council.

REFERENCES

[1] R. Parmee, W. I. Milne, and M. T. Cole, "Xray Generation using Carbon Nanotubes" *NanoConvergence*, 2014.
[2] R. Rosen, W. Simendinger, C. Debbault, H. Shimoda, L. Fleming, B. Stoner, *et al.*, "Application of carbon nanotubes as electrodes in gas discharge tubes," *Applied Physics Letters*, vol. 76, pp. 1668-1670, 2000.
[3] Y. Saito, K. Hata, A. Takakura, J. Yotani, and S. Uemura, "Field emission of carbon nanotubes and its application as electron sources of ultra-high luminance light-source devices," *Physica B: Condensed Matter*, vol. 323, pp. 30-37, 2002.
[4] S. Yahachi, U. Sashiro, and H. Koji, "Cathode Ray Tube Lighting Elements with Carbon Nanotube Field Emitters," *Japanese Journal of Applied Physics*, vol. 37, p. L346, 1998.
[5] K. B. K. Teo, M. Chhowalla, G. A. J. Amaratunga, W. I. Milne, P. Legagneux, G. Pirio, *et al.*, "Fabrication and electrical characteristics of carbon nanotube-based microcathodes for use in a parallel electron-beam lithography system," *Journal of Vacuum Science and Technology B*, vol. 21, pp. 693-697, Mar-Apr 2003.
[6] M. T. Cole, C. Li, Y. Zhang, S. G. Shivareddy, J. S. Barnard, W. Lei, *et al.*, "Hot Electron Field Emission via Individually Transistor-

Ballasted Carbon Nanotube Arrays," *ACS Nano*, vol. 6, pp. 3236-3242, Apr 2012.
[7] M. T. Cole, K. B. K. Teo, O. Groening, L. Gangloff, P. Legagneux, and W. I. Milne, "Deterministic Cold Cathode Electron Emission from Carbon Nanofibre Arrays," *Scientific Reports*, vol. 4, 2014.
[8] M. Cahay, P. T. Murray, T. C. Back, S. Fairchild, J. Boeckl, J. Bulmer, *et al.*, "Hysteresis during field emission from chemical vapor deposition synthesized carbon nanotube fibers," *Applied Physics Letters*, vol. 105, p. 173107, 2014.
[9] A. V. Arkhipov, M. V. Mishin, and I. V. Parygin, "Hysteresis of pulsed characteristics of field emission from nanocarbon materials," *Surface and Interface Analysis*, vol. 39, pp. 149-154, 2007.
[10] V. P. Mammanna, T. E. A. Santos, A. P. Mammanna, V. Baranauskas, H. J. Ceragioli, and A. C. Peterlevitz, "Field emission properties of porous diamond-like films produced by chemical vapor deposition," *Applied Physics Letters*, vol. 81, pp. 3470-3472, 2002.
[11] S. L. Yue, C. Z. Gu, C. Y. Shi, and C. Y. Zhi, "Field emission characteristics of oriented-AlN thin film on tungsten tip," *Applied Surface Science*, vol. 251, pp. 215-219, 9/15/ 2005.
[12] A. A. Kuznetsov, S. B. Lee, M. Zhang, R. H. Baughman, and A. A. Zakhidov, "Electron field emission from transparent multiwalled carbon nanotube sheets for inverted field emission displays," *Carbon*, vol. 48, pp. 41-46, 2010.
[13] J. D. Carey and S. R. P. Silva, "Conditioning of hydrogenated amorphous carbon thin films for field emission via current stressing," *Applied Physics Letters*, vol. 78, pp. 347-349, 2001.
[14] C. Li, Y. Zhang, M. Mann, P. Hiralal, H. E. Unalan, W. Lei, *et al.*, "Stable, self-ballasting field emission from zinc oxide nanowires grown on an array of vertically aligned carbon nanofibers," *Applied Physics Letters* vol. 96, p. 143114, 5 April 2010.
[15] I. Musa, D. A. I. Munindrasada, G. A. J. Amaratunga, and W. Eccleston, "Ultra-low-threshold field emission from conjugated polymers," *Nature*, vol. 395, pp. 362-365, Sep 1998.
[16] M. T. Cole, R. J. Parmee, A. Kumar, C. M. Collins, M. H. Kang, J. Xiao, *et al.*, "Conjugated polyelectrolyte nano field emission adlayers," *Nanoscale Horizons*, 2016.
[17] R. C. Smith, J. D. Carey, R. J. Murphy, W. J. Blau, J. N. Coleman, and S. R. P. Silva, "Charge transport effects in field emission from carbon nanotube-polymer composites," *Applied Physics Letters*, vol. 87, p. 263105, 2005.
[18] T. Connolly, R. C. Smith, Y. Hernandez, Y. Gun'ko, J. N. Coleman, and J. D. Carey, "Carbon-Nanotube-Polymer Nanocomposites for Field-Emission Cathodes," *Small*, vol. 5, pp. 826-831, 2009.
[19] I. Alexandrou, E. Kymakis, and G. A. J. Amaratunga, "Polymer-nanotube composites: Burying nanotubes improves their field emission properties," *Applied Physics Letters*, vol. 80, pp. 1435-1437, 2002.
[20] C. H. Poa, S. R. P. Silva, P. C. P. Watts, W. K. Hsu, H. W. Kroto, and D. R. M. Walton, "Field emission from nonaligned carbon nanotubes embedded in a polystyrene matrix," *Applied Physics Letters*, vol. 80, pp. 3189-3191, 2002.
[21] S. Coskun, B. Aksoy, and H. E. Unalan, "Polyol Synthesis of Silver Nanowires: An Extensive Parametric Study," *Crystal Growth & Design*, vol. 11, pp. 4963-4969, 2011/11/02 2011.
[22] H. Mao, J. Feng, X. Ma, C. Wu, and X. Zhao, "One-dimensional silver nanowires synthesized by self-seeding polyol process," *Journal of Nanoparticle Research*, vol. 14, pp. 1-15, 2012.
[23] L. Chen, J. M. Chabu, R. Jin, and J. Xiao, "Single gold-nanoparticles-decorated silver/carbon nanowires as substrates for surface-enhanced Raman scattering detection," *RSC Advances*, vol. 3, pp. 26102-26109, 2013.



Matthew T. Cole CEng, CPhys, CSci, obtained an MEng in Engineering Sciences from Oxford University, UK, in 2008 and a PhD in Electrical Engineering from Cambridge University, UK, in 2011. He is the Oppenheimer Research Fellow in the Electrical Engineering Division, Department of Engineering, Cambridge University. Dr Cole's research focuses on the heterogeneous integration of chemical vapor deposited aligned nanomaterials for nanoscale vacuum power electronics devices. He is a Fellow of St Edmunds College, Cambridge University.

Dr Cole he was awarded the 2015 Institute of Materials, Minerals and Mining's Silver Medal, the Institute of Engineering and Technology's Sir Royce Medal, and the Royal Academy of Engineering's Sir MacFarlane Medal. In 2016 he was named in the inaugural European Forbes 30 under 30 list.



Sahin Coskun received the BS in Metallurgy from Gazi University, Ankara, Turkey in 2007 and MSc degree in Metallurgical and Materials Engineering from Middle East Technical University (METU), Ankara, Turkey in 2012. He is currently a PhD candidate in the same department. He has been working as a teaching assistant in METU since 2008. His research interests include synthesis of metal nanostructures with different morphologies and their utilization in various opto-electronic devices.



Richard J. Parmee received the BA and MA in Electrical Sciences from Cambridge University in 1973. He is currently a PhD candidate in the Electrical Engineering Division, Department of Engineering, Cambridge University. His research interests include the application of chemical vapor deposited aligned nanomaterials for nanoscale vacuum electron sources for Xray devices. He holds the William Pitt Fellowship at Pembroke College, Cambridge University.



Pritesh Hiralal received the MPhys in Physics from the University of Manchester, UK, in 2003, and PhD in Electrical Engineering from the Department of Engineering, Cambridge University. He has spent time in industry at the Nokia Research Centre where he holds several patents. He has been a Research Associate and adjunct lecturer at the University of Cambridge. His research interests include the growth of nanomaterials and the combination of these into different architectures for photovoltaics and energy storage devices.



Cinzia Cepek obtained the PhD in Solid State Physics at the Mathematisch - naturwissenschaftlichen Fakultät der Universität Zürich in 2000. Since 2001 she has worked at the CNR-IOM (Trieste, Italy). In 2006 she became lead scientist responsible for the Analytical Division. Her research interests have focused on studying the growth mechanisms of carbon-based nano-materials and their hybrids, obtained via catalytic CVD at UHV conditions.



Alexander W. Robertson received an MPhys in Physics from the University of Durham, UK, in 2009 and a DPhil in Materials Science from the University of Oxford, UK, in 2013. He is currently a post-doctoral researcher in the Department of Materials at the University of Oxford. His research interests include nanomaterials, synthesis, material defects, and transmission electron microscopy.



Chi Li received the PhD in Engineering from Southeast University, China in 2011. From 2008 to 2010, he was a visiting researcher at the University of Cambridge where he developed novel field emission devices using patterned-aligned carbon nanotubes. In 2014 he was appointed an associate professor at National Center for Nanoscience and Technology, Beijing.



Qing Dai received the BEng and MEng from Imperial College, London, before coming to the University of Cambridge to pursue a PhD in Nanophotonics at the Department of Engineering. After completing his PhD in 2011, he continued as a Research Associate at Centre of molecular materials for photonics and electronics. Since 2012, he was recruited by the thousand talents program of China and then joined National Center for Nanoscience and Technology where he is a professor in Nanophotonics.



Jamie H. Warner obtained a PhD in Physics from the University of Queensland in 2004. He is currently Professor of Materials in the Department of Materials, Oxford University. Prof Warner is a Royal Society University Research Fellow and Visiting Professor at Sungkyunkwan University, and Heads the Nanostructured Materials Group at Oxford University.



William I. Milne FEng, FIET, FIMMM obtained a BSc from St Andrews University in Scotland in 1970 and then went on to read for a PhD in Electronic Materials at Imperial College London. He was awarded his PhD and DIC in 1973 and, in 2003, a D.Eng (Honoris Causa) from University of

Waterloo, Canada.

He was Head of Electrical Engineering, Cambridge University from 1999-2014 and Director of the Centre for Advanced Photonics and Electronics from 2004-2015. He has published/presented ~ 800 papers in the areas of large area Si and carbon based electronics, of which 200 were invited.

Prof. Milne was elected a Fellow of The Royal Academy of Engineering in 2006, was awarded the 2008 J.J. Thomson medal from the IET, and the 2010 NANOSMAT prize for excellence in nanotechnology.



H. Emrah Unalan received the BS in Metallurgical and Materials Engineering from Middle East Technical University, Turkey in 2002 and the MSs and PhD in Materials Science and Engineering at Rutgers University, USA in 2004 and 2006, respectively. From 2006 to 2008, he was a

Research Associate in the Electrical Engineering Division in the Department of Engineering, University of Cambridge, UK. In 2008, he joined the Department of Metallurgical and Materials Engineering, Middle East Technical University, where he is currently an Associate Professor.

Prof. Unalan's research interests include synthesis of nanotubes and nanowires and their utilisation in flexible, transparent, stretchable e-textiles and integrated electronics for energy harvesting devices. He is a member of Materials Research Society, American Chemical Society and a recipient of the Turkish Academy of Sciences Young Scientist Award and The Scientific and Technological Research Council of Turkey Incentive Award 2014.